

Fromto Houthalen NV

Europark 1075, 3530 Houthalen-Helchteren

BTW-nr.: BE0439.289.343

info@fromto.be | +32 11 52 04 30

Product Data Sheet

Product Code: F2-RP-90-GR-NN-20-IN

Ordering Code: 3102 (replaces 7803)

Polymer composition: PE 25-75% / PP 75-25 %

Product Description: Recy Maalgoed originates from recycled pre-sorted

municipal (household) waste and is not additivated

Application: used for injection moulding

It is not intended for use in food contact, water contact, pharmaceutical

and medical applications.



General Characteristics

Form: Regrind **Size:** < 15mm Filtration: -Color: Mixed Colors

Packaging: Delivered in Big bags (code 3102-BB)

Due to the nature of recyclates, some variation in product properties can be observed between batches. For that reason average values are indicated.

Physical & Mechanical Characteristics

Density: 910 kg/m3 (ISO 1183)

Melt Mass-Flow Rate (MFR): 4.32 g/10 min (ISO 1133 - 230°C/2.16 kg)

Tensile Modulus: 921 MPa (ISO 527-1) Tensile Strength (Yield): 20.5 MPa (ISO 527-2) Tensile Elongation (Yield): 8,4 % (ISO 527-2) **Tensile Elongation (at break)**: 8.8 % (ISO 527-2)

Impact Strength (Charpy Test) at 23°C: 7.5 kJ/m²) (ISO 179)

Version 01-10-2025

Disclaimer

The liability of FROMTO is strictly limited to the features and provisions laid out in this product data sheet. No claims, representations or warranties, whether express or implied, are made by FROMTO as to the processability of the products. Once a buyer uses, $processes \ (whether or not in combination \ with other products) \ or handles \ a \ product \ of FROMTO, FROMTO \ does \ not \ accept \ any \ kind$ of liability whatsoever as to the safety, reliability, processability, durability and performance of the products subject to usage, processing or handling.

